

TECHNICAL DATA SHEET

POLYGREEN F9250

Description :

3-functional Bio-Polyol, for the use in Polyurethane applications

Specification of POLYGREEN F9250:

Properties	Test method	Range/Value
Gardner	AOCS TD 1a-64	2.0
Hydroxyl Number, mg KOH/g	AOCS CD 13-60	110-120
Viscosity, mPa.s @ 25°C (77°F)	ASTM D 4878	800-1,200
pH	pH Meter	6.5 - 7.5
Water, %	AOCS Ca2e-84	< 0.15

Shelf Life

If stored under proper storage conditions and below 40 deg C

- 12 months in closed packaging
- 6 months when stored in bulk

Bio Content: min 99% (according to ASTM D6866-16 by Beta Analytic Inc.)

Polygreen's Bio-Polyols have been tested according to OECD 423 and OECD 404 by TUV-PSB, an independent laboratory in Singapore, and were classified as **non-toxic and non-irritant**.

NOTICE: All of the above properties, are accurate to our best knowledge at the time of publication. It is the obligation of the user to test the product for its suitability in the user's intended application. Since the conditions of use of this information or any material supplied are beyond our control, all recommendations or suggestions are made without guarantee, express or implied on our part.

PolyGreen Chemicals (Malaysia) Sdn Bhd

24, Jalan Wan Kadir 1, Taman Tun Dr. Ismail, 60000 Kuala Lumpur.

Tel : (03) 77286440 Fax : (03) 77291886 , Email: polyol@polygreen.com.my

